

Journal of Mechanics of Materials and Structures

**GEOMETRICALLY NONLINEAR COSSERAT ELASTICITY IN THE PLANE:
APPLICATIONS TO CHIRALITY**

Sebastian Bahamonde, Christian G. Böhrmer and Patrizio Neff

Volume 12, No. 5

December 2017



GEOMETRICALLY NONLINEAR COSSERAT ELASTICITY IN THE PLANE: APPLICATIONS TO CHIRALITY

SEBASTIAN BAHAMONDE, CHRISTIAN G. BÖHMER AND PATRIZIO NEFF

Modeling two-dimensional chiral materials is a challenging problem in continuum mechanics because three-dimensional theories reduced to isotropic two-dimensional problems become nonchiral. Various approaches have been suggested to overcome this problem. We propose a new approach to this problem by formulating an intrinsically two-dimensional model which does not require references to a higher dimensional one. We are able to model planar chiral materials starting from a geometrically nonlinear Cosserat-type elasticity theory. Our results are in agreement with previously derived equations of motion but can contain additional terms due to our nonlinear approach. Plane wave solutions are briefly discussed within this model.

A list of symbols can be found on page 707.

1. Introduction

Classical elasticity theory assumes structureless material points. These points are not allowed to possess an additional so-called microstructure which could take into account properties like orientation or volume of the material points. It is possible to extend the theory of classical elasticity to take into account this additional structure; this is known as the Cosserat [1909] model. In the Cosserat continuum, material points can, for instance, experience rotations without stretches. Therefore, in addition to the standard deformation field φ there is an independent rotation field \bar{R} , which means that \bar{R} is an orthogonal matrix. Many models in continuum mechanics were motivated by this idea, which has resulted in many interesting research lines, sometimes with varying names [Ericksen and Truesdell 1957; Toupin 1962; 1964; Ericksen 1962a; 1962b; 1967; Mindlin 1964; Eringen and Suhubi 1964; Suhubi and Eringen 1964; Green and Rivlin 1964; Schaefer 1967; Eringen 1999]

The three-dimensional static nonlinear Cosserat model has seen a tremendous increase of interest in recent years [Neff 2006b; Neff and Münch 2009; Münch et al. 2011; Neff et al. 2008; Fischle et al. 2017; Borisov et al. 2016; Fischle and Neff 2017c]. This is connected to its potential to model uncommon effects like lattice rotations. Working with the manifold $SO(3)$ of proper rotations requires, however, many new tools from the mathematical and implementational side. Expositions regarding the mathematical treatment can be found in [Neff 2004a; 2006a; Neff and Münch 2008; Neff et al. 2015; Lankeit et al. 2017]; similarly for computational results in [Fischle and Neff 2017a; 2017b]. The Cosserat approach is maybe best known for its ability to model thin shell structures. Here, the additional orthogonal frame provided by the Cosserat theory fits well into the theory of deformable surfaces [Neff 2004b; 2007; Neff

MSC2000: 74J35, 74A35, 74J30, 74A30.

Keywords: Cosserat continuum, geometrically nonlinear micropolar elasticity, chiral materials, planar models.

et al. 2010; Bîrsan and Neff 2013; 2014; Sander et al. 2016]. Not much is known, regrettably, in the case of general nonlinear dynamics. Our contribution [Böhmer et al. 2016] sheds some light in this direction.

One of the major unresolved issues of the theory is the precise manner in which elastic deformations (macroscopic) and Cosserat microrotations are coupled. If we consider a quadratic ansatz in the stretch tensor, it usually comes down to writing a coupling term of the form $\mu_c \|\text{skew}(\bar{U} - \mathbb{1})\|^2$, in which $\mu_c \geq 0$ is known as the Cosserat couple modulus. The effect of this coupling term is clear by increasing $\mu_c \rightarrow \infty$. Then the Cosserat rotations become the continuum rotations $R = \text{polar } F$. A similar effect can be obtained by instead considering the coupling $\mu_c \|\bar{R}^T \text{polar } F - \mathbb{1}\|^2$. Both terms induce the same linear response. It is important to note that the geometrically nonlinear Cosserat model can be used also with $\mu_c \equiv 0$, a possibility which is meaningless in the linear Cosserat model. In the case $\mu_c = 0$ one has a Cosserat model with symmetric stresses, whereas stretches may be nonsymmetric.

Cosserat elasticity is generally formulated as a three-dimensional continuum mechanics theory and planar problems are usually considered by restricting either displacements or microrotations to the plane. One sometimes speaks of the first planar problem when $\mathbf{u} = (u_1, u_2, 0)$ and rotations are constrained to be about the z -direction. The second planar problem deals with the opposite situation where $\mathbf{u} = (0, 0, u_3)$ while the rotations are constrained about the x -axis and y -axis; see for instance [Ostoja-Starzewski and Jasiuk 1995; Joumaa and Ostoja-Starzewski 2011].

Chirality¹ or handedness is a common feature in various fields of science. It refers to the possibility of an object or system to be distinguishable from its mirror image. Many molecules in chemistry are chiral, most often due to the presence of an asymmetric carbon atom. Chiral materials have been of interest in continuum mechanics since the 1980s. When one is interested in studying chiral materials [Lakes and Benedict 1982; Lakes 2001], it turns out that a three-dimensional theory when reduced to an isotropic two-dimensional problem becomes nonchiral [Lakes 2001; Rosi and Auffray 2016; Liu et al. 2012b].

Typically, a chiral term in a three-dimensional elasticity model would be of the form

$$(\bar{R}^T F)_{ij} C_{ijmn} (\bar{R}^T \text{Curl } \bar{R})_{mn}, \quad (1-1)$$

where C_{ijmn} is a material tensor; see also Appendix A. If one considers an isotropic material tensor of the form $c_1 \delta_{ij} \delta_{mn} + c_2 \delta_{im} \delta_{jn} + c_3 \delta_{in} \delta_{jm}$, then the above term yields three contributions. It turns out that these three terms identically vanish when the first Cosserat planar problem is considered². For instance, based on representation theorems [Cheverton and Beatty 1981], a total of 20 invariants were discussed, five of which are chiral according to our formulation in Appendix A. However, a direct calculation verifies that all chiral terms vanish when the deformation gradient is confined to the plane; see (2-1).

Hence, studying two-dimensional chiral materials requires a new approach. One such approach is the use of strain gradient theories; see [Rosi and Auffray 2016], for instance. Another approach goes back to [Liu et al. 2012b] where chirality was introduced in the two-dimensional setting by revisiting isotropic fourth-order tensors and identifying an extra piece in the constitutive relation. It was subsequently shown that this additional part of the elastic tensor can indeed give a meaningful model with chirality. The model

¹“I call any geometrical figure, or group of points, chiral, and say that it has chirality if its image in a plane mirror, ideally realized, cannot be brought to coincide with itself” (Lord Kelvin 1894).

²It might be possible to construct chiral terms using nonlinear functionals beyond the usual quadratic terms which yield a nontrivial planar theory.

considered in [Liu et al. 2012b] is based on linear Cosserat elasticity; see also [Liu et al. 2012a; Liu and Hu 2016].

In the present paper, we approach this problem from a very different point of view. We begin by carefully studying the basic formulation of geometrically nonlinear Cosserat elasticity in the plane by following three different routes. First, we will follow the standard approach of formulating three-dimensional Cosserat elasticity and restricting it to the plane, thereby recalling the first and second Cosserat problems, respectively. Next we will formulate an intrinsically two dimensional model. After stating the energy functional of our model, the equations of motion are rigorously derived using the calculus of variations. Our intrinsically two-dimensional formulation requires no reference to a theory in three dimensions. Within this setting we are able to introduce a new displacement vector which allows us to model planar chiral materials without the use of new constitutive relations. Our model, which is geometrically nonlinear, yields equations very similar to those reported in [Liu et al. 2012b] when we assume small rotations and small displacements. However, due to our nonlinear theory as a starting point, we find an additional contribution which naturally appears in the equations of motion.

2. The Cosserat problem in the plane

We are interested in studying the dynamical geometrically nonlinear Cosserat problem in the plane and this immediately poses the rather interesting question of how to formulate such a theory. On the one hand, one could simply start with three-dimensional Cosserat elasticity and consider an ansatz which reduces the equations to the planar case. This approach yields two different types of models, often called the first and second Cosserat planar model; see for instance [Joumaa and Ostoja-Starzewski 2011]. However, as Cosserat elasticity takes into account the possible microrotations of matter points, we must recall that rotations in the plane are very different from those in three dimensions, since the latter need not commute. An intrinsically two-dimensional model of Cosserat elasticity could thus be formulated, which would differ from the three-dimensional case restricted to the plane.

2.1. The first Cosserat planar problem. The first Cosserat planar problem is defined by $\mathbf{u} = (u_1, u_2, 0)$ and $\mathbf{a} = (0, 0, a_3)$, where the vector \mathbf{a} defines the axis of the Cosserat rotation. This means we can begin with a three-dimensional setup confined to the xy -plane, with rotations about the z -axis only. In this case the deformation is given by $\varphi = (\varphi_1(x, y), \varphi_2(x, y), z)$ so that the deformation gradient F reads

$$F = \nabla\varphi = \begin{pmatrix} \varphi_{1,x} & \varphi_{1,y} & 0 \\ \varphi_{2,x} & \varphi_{2,y} & 0 \\ 0 & 0 & 1 \end{pmatrix}. \quad (2-1)$$

Next we consider the rotations in the xy -plane. We call the angle of rotation $\phi = \phi(x, y)$, which yields

$$\bar{R} = \begin{pmatrix} \cos \phi & -\sin \phi & 0 \\ \sin \phi & \cos \phi & 0 \\ 0 & 0 & 1 \end{pmatrix}. \quad (2-2)$$

Now we can compute $\bar{R}^T \text{Curl } \bar{R}$, a useful curvature measure of the Cosserat theory [Neff and Münch 2008]. Using the index notation, it can be written as

$$(\text{Curl } \bar{R})_{ij} = \varepsilon_{jmn} \partial_m \bar{R}_{in}, \quad (2-3)$$

where ε_{jmn} is the Levi-Civita symbol. For the given orthogonal matrix (2-2) this is given by

$$\bar{R}^T \text{Curl } \bar{R} = \left(\begin{array}{cc|c} 0 & 0 & -\phi_x \\ 0 & 0 & -\phi_y \\ \hline 0 & 0 & 0 \end{array} \right). \quad (2-4)$$

At this point we already see the root cause of the problem when trying to formulate the desired theory. All the components of $\bar{R}^T \text{Curl } \bar{R}$ restricted to the plane are zero. We also note that the components of this matrix are determined by the object $\text{grad } \phi$; this means effectively a vector with two components which already points towards an intrinsically two-dimensional model.

A direct calculation establishes

$$\begin{aligned} \text{dev}(\bar{R}^T \text{Curl } \bar{R}) &= \frac{1}{2} \begin{pmatrix} 0 & 0 & -\phi_x \\ 0 & 0 & -\phi_y \\ -\phi_x & -\phi_y & 0 \end{pmatrix}, \\ \text{skew}(\bar{R}^T \text{Curl } \bar{R}) &= \frac{1}{2} \begin{pmatrix} 0 & 0 & -\phi_x \\ 0 & 0 & -\phi_y \\ \phi_x & \phi_y & 0 \end{pmatrix}, \\ \text{tr}(\bar{R}^T \text{Curl } \bar{R}) &= 0. \end{aligned} \quad (2-5)$$

The important issue at this point is that there are no planar contributions in any of the irreducible parts of $\bar{R}^T \text{Curl } \bar{R}$ in (2-5).

Also, we can compute the nonsymmetric stretch tensor, which gives

$$\bar{U} = \bar{R}^T F = \begin{pmatrix} \varphi_{1,x} \cos \phi + \varphi_{2,x} \sin \phi & \varphi_{1,y} \cos \phi + \varphi_{2,y} \sin \phi & 0 \\ \varphi_{2,x} \cos \phi - \varphi_{1,x} \sin \phi & \varphi_{2,y} \cos \phi - \varphi_{1,y} \sin \phi & 0 \\ 0 & 0 & 1 \end{pmatrix}. \quad (2-6)$$

This implies that the irreducible parts of $\bar{U} = \bar{R}^T F$ and $\bar{R}^T \text{Curl } \bar{R}$ are orthogonal in the sense that

$$\begin{aligned} \text{tr}(\bar{R}^T \text{Curl } \bar{R}) \text{tr}(\bar{R}^T F) &= 0, \\ \langle \text{dev}(\bar{R}^T \text{Curl } \bar{R}), \text{dev}(\bar{R}^T F) \rangle &= 0, \\ \langle \text{skew}(\bar{R}^T \text{Curl } \bar{R}), \text{skew}(\bar{R}^T F) \rangle &= 0. \end{aligned} \quad (2-7)$$

This implies that we cannot construct interaction terms between the displacements and the microrotations. Interaction terms of the above form were considered in [Böhmer and Tamanini 2015; Böhmer et al. 2016]. These terms allow for a natural coupling between elastic deformations and the microrotations which, for instance, gives rise to soliton solutions; see [Böhmer et al. 2016].

Let us also remark that in case of the finite theory one may as well consider the irreducible components of $F^T F$ rather than $\bar{R}^T F$. The form of F given in (2-1) implies that $F^T F$ will be the same form as \bar{U} given by (2-6). Hence, all inner product considered in (2-7) would also vanish which implies that it is also not possible to construct interaction terms in the finite theory.

However, one can still construct interaction terms, albeit less natural ones. Consider the Frobenius norm of the dislocation density tensor

$$\|(\bar{R}^T \text{Curl } \bar{R})\|^2 = \phi_x^2 + \phi_y^2, \quad (2-8)$$

which agrees with the vector norm of $\text{grad } \phi$. Hence, the only option to construct an interaction term would be to consider an expression of the form

$$V_{\text{interaction}} \propto \|(\bar{R}^T \text{Curl } \bar{R})\| \text{tr}(\bar{R}^T F). \quad (2-9)$$

An interaction of this type is quite unnatural since we are not considering the inner products of objects in the same irreducible spaces, which is what led to (2-7). From a more mathematical point of view, the presence of the square root in (2-9) might cause differentiability issues when the orthogonal matrix \bar{R} approaches a constant rotation.

It is also clear from (2-6) that the polar part of any deformation tensor restricted to the plane will be of the same form as the rotation matrix (2-2) which means we could, in principle, construct the Cosserat couple term which contains the term $\bar{R}^T \text{polar } F$.

2.2. The second Cosserat planar problem. The second Cosserat planar problem is defined by $\mathbf{u} = (0, 0, u_3)$ and $\mathbf{a} = (a_1, a_2, 0)$. This means $\varphi = (x, y, \varphi_3(t, x, y))$, so that elastic displacements are only allowed along the direction perpendicular to the plane. The rotations can be about the x -axis and the y -axis in this case. While this is mathematically well-defined, this is less well motivated than the first Cosserat problem from a practical point of view.

The deformation gradient of the second Cosserat planar model is given by

$$F = \nabla \varphi = \begin{pmatrix} 1 & 0 & 0 \\ 0 & 1 & 0 \\ \varphi_{3,x} & \varphi_{3,y} & 1 \end{pmatrix}. \quad (2-10)$$

Next we consider the rotations about the x and about the y axes. We call the respective angles of rotation $\alpha = \alpha(t, x, y)$ and $\beta = \beta(t, x, y)$ so that

$$\bar{R} = \begin{pmatrix} \alpha^2/\ell^2 + \cos \ell \beta^2/\ell^2 & (1 - \cos \ell)\alpha\beta/\ell^2 & \sin \ell \beta/\ell \\ (1 - \cos \ell)\alpha\beta/\ell^2 & \cos \ell \alpha^2/\ell^2 + \beta^2/\ell^2 & -\sin \ell \alpha/\ell \\ -\sin \ell \beta/\ell & \sin \ell \alpha/\ell & \cos \ell \end{pmatrix}, \quad (2-11)$$

where $\ell = \sqrt{\alpha^2 + \beta^2}$. Due to the more complicated structure of the rotation matrix, the second Cosserat planar problem differs from the first problem substantially. This is due to our geometrically nonlinear setup which allows for large rotations. The explicit form of $\bar{R}^T \text{Curl } \bar{R}$ is rather involved and therefore we will not state it explicitly. It suffices to mention that the only vanishing components are $(\bar{R}^T \text{Curl } \bar{R})_{31} = (\bar{R}^T \text{Curl } \bar{R})_{32} = 0$. It is instructive, however, to consider this quantity assuming small rotations $\alpha, \beta \ll 1$, in which case one finds

$$\bar{R}^T \text{Curl } \bar{R} \simeq \begin{pmatrix} \beta_y & -\beta_x & 0 \\ -\alpha_y & \alpha_x & 0 \\ 0 & 0 & \alpha_x + \beta_y \end{pmatrix}. \quad (2-12)$$

One interesting aspect of this equation is the presence of the (zz) components. When linear Cosserat elasticity is considered, as in [Joumaa and Ostoja-Starzewski 2011], then the curvature tensor does not have this component and is indeed restricted to the plane. In the nonlinear setting this is no longer the case which also motivates a different approach to the planar case.

It is clear that the stretch tensor $\bar{U} = \bar{R}^T F$ is not orthogonal to any of the components of $\bar{R}^T \text{Curl } \bar{R}$. Therefore the aforementioned coupling terms could in principle be constructed. However, this construction appears to be quite unnatural when compared to the first Cosserat problem.

The conceptual problem of using either the first or the second Cosserat planar model is simply that both theories differ considerably, and also differ from the nonlinear theory. This motivates us to formulate an intrinsically two-dimensional model which does not refer to the three-dimensional setting altogether.

3. Intrinsic planar model

3.1. Basic quantities. In order to formulate an intrinsically two-dimensional model we simply begin with the two-dimensional deformation vector $\varphi = (\varphi_1, \varphi_2)$ so that the deformation gradient reads

$$F = \nabla \varphi = \begin{pmatrix} \varphi_{1,x} & \varphi_{1,y} \\ \varphi_{2,x} & \varphi_{2,y} \end{pmatrix}. \quad (3-1)$$

Similar to rotations about the z -axis in the first Cosserat planar model, we consider a two-dimensional rotation matrix where, as before, we call the angle $\vartheta = \vartheta(x, y)$ so that

$$\bar{R} = \begin{pmatrix} \cos \vartheta & -\sin \vartheta \\ \sin \vartheta & \cos \vartheta \end{pmatrix}. \quad (3-2)$$

These definitions are purely two-dimensional and do not require the higher dimensional setting. However, as expected, the components of the intrinsic deformation gradient are identical to the planar components of the corresponding three-dimensional one; see (2-1). Likewise, the intrinsic rotation matrix has the planar components of the three-dimensional rotation matrix (2-2) of the first Cosserat planar problem.

The first object which requires a more careful approach is the matrix curl of the curvature measure. In three dimensions the matrix curl requires the object ε_{jmn} , see (2-3). However, the Levi-Civita tensor ε_{jmn} is a three-dimensional object which has no geometrical meaning in any dimension other than three. Therefore, one has to change this definition and adopt it to the planar case.

Let us begin by recalling the lesser-known fact that the vector curl is sometimes introduced in two dimensions to give a scalar quantity. Consequently, one would expect the two-dimensional matrix curl to give a vector. It turns out that this follows quite naturally when the Levi-Civita symbol in two dimensions is considered. Namely, it has two indices ε_{ij} , instead of ε_{ijk} in three dimensions. Hence, the contraction of the partial derivative of a matrix with the Levi-Civita gives a vector. This leads us to define the two-dimensional matrix curl $\bar{R}^T \text{Curl } \bar{R}$ in the following way:

$$(\text{Curl } \bar{R})_i := \varepsilon_{rs} \partial_r \bar{R}_{is}. \quad (3-3)$$

This matrix curl maps matrices to vectors, as expected.

This definition is quite natural in the present context as can be seen by computing the quantity $\bar{R}^T \text{Curl } \bar{R}$, which then becomes

$$\bar{R}^T \text{Curl } \bar{R} = \begin{pmatrix} \vartheta_x \\ \vartheta_y \end{pmatrix} = \text{grad } \vartheta. \quad (3-4)$$

This result contains the two nonvanishing components of the three-dimensional object $\bar{R}^T \text{Curl } \bar{R}$; compare with (2-4).

Now, we are faced with a similar problem as before: we cannot simply couple the two-dimensional vector (the two-dimensional Cosserat curvature measure) to the deformation gradient which is, of course, a 2×2 matrix. However, we can proceed as follows. Let us write any vector \mathbf{v} as $\mathbf{v} = |\mathbf{v}|\hat{\mathbf{v}}$, which we can view as the irreducible decomposition of the vector into a scalar $|\mathbf{v}|$ and a direction $\hat{\mathbf{v}}$ with $|\hat{\mathbf{v}}| = 1$. Applied to the vector $\bar{\mathbf{R}}^T \text{Curl } \bar{\mathbf{R}}$, we can consider the scalar quantity $\|\bar{\mathbf{R}}^T \text{Curl } \bar{\mathbf{R}}\|$ which can be coupled to the trace part of the deformation gradient. Hence, we can consider the term

$$V_{\text{interaction}} \propto \text{tr}(\bar{\mathbf{R}}^T F) \|\bar{\mathbf{R}}^T \text{Curl } \bar{\mathbf{R}}\|, \quad (3-5)$$

which in the two-dimensional setting is a natural choice. We recall that in the three-dimensional case we could write a very similar term, namely (2-9), however, it was not well justified in that setting.

The main point to note is that modeling planar material requires, independently of the approach, two geometrically different quantities: Matrix-valued objects (which describe the elastic deformations) and vectors (which describe the rotations about the axis perpendicular to the material). Any model which attempts at introducing interactions between these two quantities needs to address the principal issue of how such couplings can be achieved.

Since $\bar{\mathbf{R}}$ is still an orthogonal matrix, it appears best to consider the coupling based on $\bar{\mathbf{R}}^T$ polar F , which does not involve conceptual problems in either dimensions two or three.

The Cosserat model is cast in a variational framework on the reference configuration. The dynamical equations follow from a generalized Hamiltonian principle. A replacement of the first Piola–Kirchhoff tensor of classical nonlinear elasticity is easily seen to be $\partial V / \partial F_{ij}$ with V being the energy function of the model considered.

3.2. Elastic energy and curvature energy. We write the energy functional for the elastic deformation as

$$V_{\text{elastic}}(F, \bar{\mathbf{R}}) = \mu \|\text{sym } \bar{\mathbf{R}}^T F - \mathbf{1}\|^2 + \frac{1}{2} \lambda (\text{tr}(\text{sym}(\bar{\mathbf{R}}^T F) - \mathbf{1}))^2, \quad (3-6)$$

where λ and μ are the standard elastic Lamé parameters in two dimensions. For the dynamical treatment, we will need to subtract kinetic energy, which we assume to be of the form $\frac{1}{2} \rho \|\dot{\phi}\|^2$.

The three-dimensional energy functional of the microrotations $V_{\text{rotational}}$ is based on the energy functional containing $\|\bar{\mathbf{R}}^T \text{Curl } \bar{\mathbf{R}}\|_{\mathbb{R}^{3 \times 3}}^2$. It is natural to consider the same functional form in two dimensions using the matrix curl defined in \mathbb{R}^2 , as in (3-3).

Using the previously stated (3-4), we write the two-dimensional curvature energy as

$$V_{\text{curvature}}(\nabla \vartheta) = \mu L_c^2 \|\bar{\mathbf{R}}^T \text{Curl } \bar{\mathbf{R}}\|_{\mathbb{R}^2}^2 = \mu L_c^2 \|\text{grad } \vartheta\|_{\mathbb{R}^2}^2, \quad (3-7)$$

where L_c is the characteristic length and μ is the shear modulus from above. We emphasize that this (vector) norm is computed in two dimensions by using the subscript \mathbb{R}^2 ; this is to avoid confusion with the 3D (matrix) norm in $\mathbb{R}^{3 \times 3}$. The simple form of the energy when expressed in vector form is in fact expected as rotations in the plane are characterized by only one angle ϑ .

In order to study the dynamical problem, we will need to subtract kinetic energy, which we assume to be of the form $\rho_{\text{rot}} \|\dot{\vartheta}\|^2$ where ρ_{rot} is the scalar rotational density. One could also choose the kinetic energy as $\text{tr}(\dot{\bar{\mathbf{R}}}^T \dot{\bar{\mathbf{R}}})$ as this is somewhat more natural; however, a direct calculation gives that $\text{tr}(\dot{\bar{\mathbf{R}}}^T \dot{\bar{\mathbf{R}}}) = 2 \|\dot{\vartheta}\|^2$, which means that they only differ by a factor of 2.

3.3. Interaction and coupling terms. Next, we wish to introduce a coupling between the elastic displacements and the microrotations. To do so, we will “couple” the irreducible parts of the elastic deformation with the microrotations. This gives

$$V_{\text{interaction}}(F, \bar{R}) = \mu L_c \chi \|\bar{R}^T \text{Curl } \bar{R}\| \text{tr}(\bar{R}^T F), \quad (3-8)$$

where χ is the coupling constant which was first introduced in [Böhmer and Tamanini 2015; Böhmer et al. 2016].

Finally, we will consider the Cosserat couple term we assume to be given by

$$V_{\text{coupling}}(F, \bar{R}) = \mu_c \|\bar{R}^T \text{polar } F - \mathbb{1}\|^2, \quad (3-9)$$

where $\mu_c \geq 0$ is the Cosserat couple modulus. Alternatively, one can consider the coupling

$$V_{\text{coupling}(2)}(F, \bar{R}) = \mu_c \|\text{skew}(\bar{R}^T F - \mathbb{1})\|^2, \quad (3-10)$$

which induces the same linear response as the coupling containing the polar part.

The complete static model is therefore given by

$$\begin{aligned} V &= V_{\text{elastic}} + V_{\text{curvature}} + V_{\text{interaction}} + V_{\text{coupling}} \\ &= \mu \|\text{sym}(\bar{R}^T F - \mathbb{1})\|_{\mathbb{R}^{2 \times 2}}^2 + \frac{1}{2} \lambda (\text{tr}(\text{sym}(\bar{R}^T F - \mathbb{1})))^2 + \mu L_c^2 \|\bar{R}^T \text{Curl } \bar{R}\|_{\mathbb{R}^2}^2 \\ &\quad + \mu L_c \chi \|\bar{R}^T \text{Curl } \bar{R}\|_{\mathbb{R}^2} \text{tr}(\bar{R}^T F) + \mu_c \|\bar{R}^T \text{polar } F - \mathbb{1}\|_{\mathbb{R}^{2 \times 2}}^2. \end{aligned} \quad (3-11)$$

Where necessary, we indicated the space over which the norm has to be computed. This is only to clarify this expression as it should be clear from the context which is the appropriate space.

3.4. Modeling to chiral lattices. The proposed intrinsic model can be applied to chiral lattices. It turns out that considering small elastic displacements and small microrotations leads to a model very similar to the one studied in [Liu et al. 2012b] with an additional term contributing to the dynamics of the microrotations. In order to allow for chirality to be incorporated into our approach we define the quantity

$$u_i^* = \varepsilon_{ij} u_j. \quad (3-12)$$

In the three-dimensional setting one could not construct a term like this as the object ε_{ij} is intrinsically two-dimensional. The corresponding term in three dimensions is ε_{ijk} which would map the vector u_k to a matrix. The two-dimensional Levi-Civita symbol ε_{ij} is identical to our rotation matrix \bar{R} for $\vartheta = -\pi/2$. This means we can write

$$\varepsilon = \begin{pmatrix} 0 & 1 \\ -1 & 0 \end{pmatrix}. \quad (3-13)$$

Thus, the vector \mathbf{u}^* is the vector \mathbf{u} rotated by 90° in the counterclockwise direction and is given by

$$\mathbf{u}^* = \varepsilon \mathbf{u} = \begin{pmatrix} 0 & 1 \\ -1 & 0 \end{pmatrix} \begin{pmatrix} u_1 \\ u_2 \end{pmatrix} = \begin{pmatrix} u_2 \\ -u_1 \end{pmatrix}. \quad (3-14)$$

Now we define the corresponding deformation gradient of the rotated vector

$$F^* = \mathbb{1} + \nabla \mathbf{u}^*, \quad (3-15)$$

so that we can define a corresponding elastic energy

$$V_{\text{elastic}}^*(F^*, \bar{R}) = \mu^* \|\text{sym } \bar{R}^T F^* - \mathbb{1}\|^2 + \frac{1}{2} \lambda^* (\text{tr}(\text{sym}(\bar{R}^T F^*) - \mathbb{1}))^2 + \mu_c^* \|\text{skew}(\bar{R}^T F^* - \mathbb{1})\|^2. \quad (3-16)$$

The use of F^* in this new elastic energy is the only difference to (3-6). This means we are introducing a new elastic energy which depends on the rotated vector \mathbf{u}^* . Let us emphasize again that an analogous construction in three dimensions cannot be achieved.

Due to these new terms based on \mathbf{u}^* , we can also define the following mixing terms

$$V_{\text{mixing}} = m_1 \text{tr}[(\text{sym}(\bar{R}^T F^*) - \mathbb{1})^T (\text{sym}(\bar{R}^T F) - \mathbb{1})] + m_2 \text{tr}(\bar{R}^T F^* - \mathbb{1}) \text{tr}(\bar{R}^T F - \mathbb{1}), \quad (3-17)$$

where we note that we could also introduce a third mixing term of the form

$$m_3 \text{tr}[(\text{skew}(\bar{R}^T F^* - \mathbb{1}))^T (\text{skew}(\bar{R}^T F - \mathbb{1}))].$$

As this term will not be required in what follows, we will neglect this contribution henceforth.

Putting together everything that is needed to model chiral effects leads to the energy functional

$$V_{\text{chiral}}(F, F^*, \bar{R}) = V_{\text{curvature}} + V_{\text{elastic}} + V_{\text{elastic}}^* + V_{\text{mixing}} + V_{\text{coupling}(2)}. \quad (3-18)$$

4. Equations of motion

In the following subsections we will state the equations of motion of our model which are derived using the calculus of variations. While most of this is fairly standard from a mathematical point of view, it is instructive to provide enough detail of this derivation, most of which can be found in Appendix B. We work predominantly in the matrix notation and we also need to consider variations with respect to the polar part of the deformation gradient, which is a nonstandard result. Also our use of matrix curls and matrix divergences requires a careful treatment, which is shown.

4.1. Field equations without chiral terms. The complete variational energy functional of the nonlinear Cosserat micropolar theory in 2D will be the sum of each variational term, so we have

$$\delta V = \delta V_{\text{curvature}} + \delta V_{\text{elastic}} + \delta V_{\text{interaction}} + \delta V_{\text{coupling}}. \quad (4-1)$$

Rotations in two dimensions depend only on one angle and one can verify that

$$\delta \bar{R} = -(\cos \vartheta \epsilon + \sin \vartheta I) \delta \vartheta = -\epsilon \bar{R} \delta \vartheta, \quad (4-2)$$

where ϵ is the 2D Levi-Civita matrix. While we computed the variations with respect to δF , we are in fact interested in the variations with respect to the displacements δu . So, let M be an arbitrary matrix; then we can easily find the relation between δF and δu which is given by

$$\langle A, \delta F \rangle = A : \delta F = -(\text{Div } M) \delta u, \quad (4-3)$$

or in other words, we need to integrate by parts once more to arrive at the equations of motions in the displacements.

We can now use (4-2) and (4-3) to rewrite the variations of Appendix B as follows:

$$\begin{aligned} \delta V_{\text{elastic}} = & -(\mu F \bar{R}^T F - 2(\mu + \lambda)F + \lambda \operatorname{tr}(\bar{R}^T F)F) : (\epsilon \bar{R}) \delta \vartheta \\ & - \operatorname{Div}[\mu(\bar{R} F^T \bar{R} + F) - 2(\mu + \lambda)\bar{R} + \lambda \operatorname{tr}(\bar{R}^T F)\bar{R}] \delta u, \end{aligned} \quad (4-4)$$

$$\delta V_{\text{curvature}} = -2\mu L_c^2 \operatorname{div}(\operatorname{grad} \vartheta) \delta \vartheta, \quad (4-5)$$

$$\begin{aligned} \delta V_{\text{interaction}} = & -\mu L_c \chi \left(\operatorname{div} \left[\operatorname{tr}(\bar{R}^T F) \frac{\operatorname{grad} \vartheta}{\|\operatorname{grad} \vartheta\|} \right] + \|\operatorname{grad} \vartheta\| F \right) : (\epsilon \bar{R}) \delta \vartheta \\ & - \mu L_c \chi \operatorname{Div}[\|(\operatorname{grad} \vartheta)\| \bar{R}] \delta u, \end{aligned} \quad (4-6)$$

$$\delta V_{\text{coupling}} = 2\mu_c \operatorname{polar} F : (\epsilon \bar{R}) \delta \vartheta + 2\mu_c \operatorname{Div} \left[\frac{1}{\operatorname{tr}(U)} (\bar{R} - \operatorname{polar} F \bar{R}^T \operatorname{polar} F) \right] \delta u. \quad (4-7)$$

4.2. Fully nonlinear equations without chiral terms. The variations with respect to our two dynamical variables, the vector u and the scalar ϑ , give two Euler–Lagrange equations. The equations of motion including kinetic energy for the displacement vector u are now written in their final form, which is

$$\begin{aligned} \rho u_{tt} = & \operatorname{Div} \left[2\mu \bar{R} \operatorname{sym}(\bar{R}^T F) + \lambda \operatorname{tr}(\bar{R}^T F) \bar{R} - 2(\mu + \lambda) \bar{R} \right. \\ & \left. + \frac{4\mu_c}{\operatorname{tr}(\sqrt{F^T F})} \operatorname{polar} F \operatorname{skew}(\bar{R}^T \operatorname{polar} F) + \mu L_c \chi \|(\bar{R}^T \operatorname{Curl} \bar{R})\| \bar{R} \right]. \end{aligned} \quad (4-8)$$

Here we used the useful identities $2 \operatorname{polar} F \operatorname{skew}(\bar{R}^T \operatorname{polar} F) = -\bar{R} + \operatorname{polar} F \bar{R}^T \operatorname{polar} F$, and moreover, $2\bar{R} \operatorname{sym}(\bar{R}^T F) = \bar{R} F^T \bar{R} + F$.

Before stating the equation of motion for the rotation, let us have a closer look at the various terms. The first line corresponds to the equations of nonlinear elasticity and the second line contains the interaction term and the Cosserat couple term.

Variations with respect to the rotation yield the following equation of motion:

$$\begin{aligned} \rho_{\text{rot}} \vartheta_{tt} = & \mu L_c^2 \operatorname{div}(\bar{R}^T \operatorname{Curl} \bar{R}) - (\mu + \lambda) \operatorname{tr}(\epsilon \bar{R}^T F) + \frac{1}{2} \mu \operatorname{tr}(\epsilon (\bar{R}^T F)^2) + \frac{1}{2} \lambda \operatorname{tr}(\bar{R}^T F) \operatorname{tr}(\epsilon \bar{R}^T F) \\ & + \frac{1}{2} \mu L_c \chi \left\{ \operatorname{div} \left[\frac{\bar{R}^T \operatorname{Curl} \bar{R}}{\|\bar{R}^T \operatorname{Curl} \bar{R}\|} \operatorname{tr}(\bar{R}^T F) \right] + \|(\bar{R}^T \operatorname{Curl} \bar{R})\| \operatorname{tr}(\epsilon \bar{R}^T F) \right\} - \mu_c \operatorname{tr}(\epsilon \bar{R}^T \operatorname{polar} F). \end{aligned} \quad (4-9)$$

The most complicated term comes from the interaction term and, in particular, the presence of the square-root when we work with the norm of $\bar{R}^T \operatorname{Curl} \bar{R}$. One has to be careful with this term as the square root is not differentiable at the origin. Due to the nonlinear nature of these equations it is very difficult to find explicit solutions or make generic statements about such solutions.

4.3. Fully nonlinear equations of the chiral model. The complete variational energy functional of the nonlinear Cosserat micropolar theory with chiral terms is given by

$$\delta V = \delta V_{\text{curvature}} + \delta V_{\text{elastic}} + \delta V_{\text{elastic}}^* + \delta V_{\text{mixing}} + \delta V_{\text{coupling}(2)}. \quad (4-10)$$

The equations of motion of the chiral model for the displacement \mathbf{u} are given by

$$\begin{aligned} \rho u_{tt} = & \text{Div}[2\mu \bar{R} \text{sym}(\bar{R}^T F) + \lambda \text{tr}(\bar{R}^T F) \bar{R} - 2(\mu + \lambda) \bar{R} + \mu_c (F - \bar{R} F^T \bar{R})] \\ & - \text{Div}[\mu^* (\bar{R} (F^*)^T \bar{R} + F^*) - 2(\mu^* + \lambda^*) \bar{R} + \lambda^* \text{tr}(\bar{R}^T F^*) \bar{R} + \mu_c^* (\bar{R} (F^*)^T \bar{R} - F^*)] : \epsilon \\ & - \text{Div}[\frac{1}{2} m_1 (\epsilon^T \bar{R} F^T \bar{R} + \bar{R} (F^*)^T \bar{R} + F : \epsilon + F^* - 2(\bar{R} : \epsilon + \bar{R})) \\ & \quad + m_2 (\text{tr}(\bar{R}^T F^*) R + \text{tr}(\bar{R}^T F) (R : \epsilon) - (\bar{R} : \epsilon + \bar{R})) \\ & \quad + \frac{1}{2} m_3 (F : \epsilon + F^* - (F \bar{R}^T \epsilon^T F + \epsilon^T F \bar{R} F))]. \end{aligned} \quad (4-11)$$

Additionally, the equation of motion for ϑ_{tt} is given by

$$\begin{aligned} \rho_{\text{rot}} \vartheta_{tt} = & \mu L_c^2 \text{div}(\bar{R}^T \text{Curl} \bar{R}) - (\mu + \lambda) \text{tr}(\epsilon \bar{R}^T F) + \frac{1}{2} \mu \text{tr}(\epsilon (\bar{R}^T F)^2) \\ & + \frac{1}{2} \lambda \text{tr}(\bar{R}^T F) \text{tr}(\epsilon \bar{R}^T F) + \mu_c \text{tr}(\epsilon \bar{R}^T F \bar{R}^T) \\ & + [\mu^* F^* \bar{R}^T F^* - 2(\mu^* + \lambda^*) F^* + \lambda^* \text{tr}(\bar{R}^T F^*) F^* + \mu_c^* F^* \bar{R}^T F^* \\ & \quad + \frac{1}{2} m_1 (F \bar{R}^T \epsilon^T F + \epsilon^T F \bar{R} F - 2(F + F^*)) \\ & \quad + m_2 (\text{tr}(\bar{R}^T F^*) F + \text{tr}(\bar{R}^T F) F^* - (F + F^*)) \\ & \quad - \frac{1}{2} m_3 (F \bar{R}^T \epsilon^T F + \epsilon^T F \bar{R} F)] : (-\epsilon \bar{R}). \end{aligned} \quad (4-12)$$

Before having a closer look at these equations and discussing applications to chiral lattices, we will briefly state two special solutions to the equations without chiral terms.

4.4. Special solution — no displacements, static and homogeneous microrotations. One of the simplest possible solutions can be sought in the form $\mathbf{u} \equiv 0$ and $\vartheta = \vartheta_0$, where ϑ_0 is a constant angle. Using this ansatz, the equations for the displacements (4-8) are identically satisfied. Equation (4-9) for the microrotations reduces to the simple equation

$$(\lambda + \mu + \mu_c - (\lambda + \mu) \cos \vartheta_0) \sin \vartheta_0 = 0. \quad (4-13)$$

This equation has two somewhat trivial solutions when $\vartheta_0 = 0$ or $\vartheta = \pi$. These correspond to all the oriented material points to be aligned horizontally. Interestingly, there are more solutions, and their properties depend on the value of the Cosserat couple modulus μ_c . If $\mu_c = 0$, then (4-13) is also satisfied by $\vartheta_0 = \frac{1}{2}\pi$ or $\vartheta_0 = \frac{3}{2}\pi$ which corresponds to all the oriented material points to be aligned vertically.

On the other hand, if $\mu_c > 0$, then we find

$$\cos \vartheta_0 = 1 + \frac{\mu_c}{\lambda + \mu}, \quad (4-14)$$

for which a solution exists provided that $\lambda + \mu \leq 0$. This, however, contradicts the standard assumptions of linear elasticity. These results appear to be consistent with our expectations of the theory.

4.5. Special solution — no displacements, static and homogeneous microrotations with chiral terms. Next, let us consider $\mathbf{u} \equiv 0$ and $\vartheta = \vartheta_0$ in the equations with chiral terms. The equations for the displacements (4-8) are again identically satisfied. Equation (4-9) for the microrotations reduces to

$$\begin{aligned} [-m_1 - 2m_2 - \lambda + \lambda^* - \mu - \mu_c + \mu^* \\ + (m_1 + 2m_2 - m_3 - \mu_c - \mu_c^* + \lambda + \lambda^* + \mu + \mu^*) \cos \vartheta_0] \sin \vartheta_0 = 0, \end{aligned} \quad (4-15)$$

where we also include the chiral and the mixing terms. As before, this equation has two trivial solutions when $\vartheta_0 = 0$ or $\vartheta = \pi$. Lastly,

$$\cos \vartheta_0 = 1 + \frac{\mu_{c1} + \mu_c + \mu_c^* - 2\lambda^* - 2\mu^* + m_3}{\lambda + \lambda^* + \mu + \mu^* - \mu_c - \mu_c^* + m_1 + 2m_2 - m_3}, \quad (4-16)$$

for which a solution exists provided that the fraction is between 0 and -2 . Due to the extra parameters present in this theory there is no *a priori* reason for this equation to have no solutions.

5. Applications to chiral lattices

Finally, we are able to demonstrate that our intrinsic two-dimensional model is applicable to chiral lattices. In doing so it is shown that it may not be necessary to begin with a three-dimensional theory and reduce it to the plane.

5.1. Equations of motion. By assuming small microrotations and small elastic displacements, we arrive at the following set of equations where we rescaled $\rho_{\text{rot}} = \frac{1}{4}\varrho_{\text{rot}}$ to match the factors used in [Liu et al. 2012b] and also introduce $\vartheta = -\phi$. This gives

$$\begin{aligned} \rho \frac{\partial^2 u_1}{\partial t^2} = & (\lambda + 2\mu + \mu^* + \mu_c^*)u_{1,xx} + (\mu + \mu_c + \lambda^* + 2\mu^*)u_{1,yy} + (\lambda + \mu - \mu_c - \lambda^* - \mu^* + \mu_c^*)u_{2,xy} \\ & + \left(\frac{1}{2}m_1 + m_2\right)(-2u_{1,xy} + u_{2,xx} - u_{2,yy}) - 2(2\lambda^* + 2\mu^* - \mu_c^*)\phi_x + 2\mu_c\phi_y, \end{aligned} \quad (5-1)$$

and the second equation

$$\begin{aligned} \rho \frac{\partial^2 u_2}{\partial t^2} = & (\mu + \mu_c + \lambda^* + 2\mu^*)u_{2,xx} + (\lambda + 2\mu + \mu^* + \mu_c^*)u_{2,yy} + (\lambda + \mu - \mu_c - \lambda^* - \mu^* + \mu_c^*)u_{1,xy} \\ & + \left(\frac{1}{2}m_1 + m_2\right)(u_{1,xx} - u_{1,yy} + 2u_{2,xy}) - 2\mu_c\phi_x - 2(2\lambda^* + 2\mu^* - \mu_c^*)\phi_y. \end{aligned} \quad (5-2)$$

Lastly, the equation for the microrotations is given by

$$\begin{aligned} \varrho_{\text{rot}} \frac{\partial^2 \phi}{\partial t^2} = & 2d_1(\phi_{xx} + \phi_{yy}) + 4(2\lambda^* + 2\mu^* - \mu_c^* - \mu_c)\phi + 2\mu_c(u_{2,x} - u_{1,y}) \\ & - 2(\mu_c^* - 2\lambda^* - 2\mu^*)(u_{1,x} + u_{2,y}). \end{aligned} \quad (5-3)$$

Setting $2d_1 = \gamma$, $\mu^* = -\mu_c^* = A$, $\lambda^* = -2A$, and $\frac{1}{2}m_1 + m_2 = -A$, we recover the equations reported in [Liu et al. 2012b, (17)]. The only difference is an additional term in the rotational equation; namely this becomes

$$\varrho_{\text{rot}} \frac{\partial^2 \phi}{\partial t^2} = \gamma(\phi_{xx} + \phi_{yy}) - 4(\mu_c + A)\phi + 2\mu_c(u_{2,x} - u_{1,y}) - 2A(u_{1,x} + u_{2,y}), \quad (5-4)$$

where the term $-4A\phi$ is the additional contribution. We believe that this term is present due to our starting point being the fully nonlinear model. Consequently, when studying plane wave solutions of this modified model, we expect some changes with respect to the wave speeds and the ratio of the amplitudes of the elastic waves, as will be discussed henceforth. It appears that our model can also be used in the context of tetrachiral lattices; see the equations of motion reported in [Chen et al. 2014].

5.2. Plane wave solutions for the chiral model. Along the lines of [Böhmer et al. 2011; 2016; Liu et al. 2012b; Böhmer and Obukhov 2012; Böhmer and Tamanini 2015], for instance, we can now study plane wave solutions of our more general model. For concreteness, let us consider a plane wave in the x -direction only. Then our ansatz for the displacements and microrotations is taken to be

$$\begin{pmatrix} u \\ v \\ \phi \end{pmatrix} = \begin{pmatrix} \hat{u} \\ \hat{v} \\ \hat{\phi} \end{pmatrix} e^{ikx - i\omega t}, \quad (5-5)$$

where k is the wave number and ω is the angular frequency. The quantities \hat{u} , \hat{v} , $\hat{\phi}$ denote the corresponding amplitudes. Substituting (5-5) into the equations of motion by replacing this form in (5-1)–(5-3) and using the above renaming of constants $2d_1 = \gamma$, $\mu^* = -\mu_c^* = A$, $\lambda^* = -2A$, $\frac{1}{2}m_1 + m_2 = -A$, we can rewrite the equations in the following form:

$$\begin{pmatrix} k^2(\lambda + 2\mu) - \rho\omega^2 & -Ak^2 & 2iAk \\ -Ak^2 & k^2(\mu_c + \mu) - \rho\omega^2 & -2ik\mu_c \\ -2iAk & 2ik\mu_c & (\gamma k^2 + 4\mu_c + 4A) - \varrho_{\text{rot}}\omega^2 \end{pmatrix} \begin{pmatrix} \hat{u} \\ \hat{v} \\ \hat{\phi} \end{pmatrix} = 0. \quad (5-6)$$

As one would expect, the above equation is very similar to the one reported in [Liu et al. 2012b] with the difference of the additional term $4A$ in the final component of the matrix. It is straightforward to show that the ratio of the amplitudes of the displacements is given by

$$\frac{\hat{u}}{\hat{v}} = \frac{A(k^2\mu - \rho\omega^2)}{A^2k^2 - \mu_c(k^2(\lambda + 2\mu) - \rho\omega^2)}. \quad (5-7)$$

Next, let us find the dispersion relation using this ratio, which gives

$$v = \frac{\omega}{k} = \sqrt{\frac{\hat{u}/\hat{v}(\mu_c(\lambda + 2\mu) - A^2) + A\mu}{\rho(\mu_c\hat{u}/\hat{v} + A)}}. \quad (5-8)$$

The two interesting limits of this relation are when the ratio of the amplitudes is either very small or very large. In these cases we find

$$v_t := v_{\hat{u}/\hat{v} \rightarrow 0} = \sqrt{\mu/\rho}, \quad (5-9)$$

which is the well-known speed for the transversal elastic wave. Likewise,

$$v_l := v_{\hat{u}/\hat{v} \rightarrow \infty} = \sqrt{\frac{\lambda + 2\mu}{\rho} - \frac{A^2}{\rho\mu_c}}, \quad (5-10)$$

so that we note that the longitudinal wave's speed is decreased by the chiral term A . The dispersion relation is shown in Figure 1. For this wave speed to be positive requires that the constant A satisfies the inequality

$$A^2 > \mu_c(\lambda + 2\mu). \quad (5-11)$$

Finally, we can consider the specific case where we only have displacements for the horizontal direction u , so that $v = 0$. In this case we use the ansatz $u = \hat{u} \cos(kx - \omega t + \delta_u)$ and $\phi = \hat{\phi} \cos(kx - \omega t + \delta_\phi)$.




Figure 1. Visualization of the dispersion relation (5-8) as a function of the ratio of amplitudes \hat{u}/\hat{v} . The dashed lines indicate the limiting cases when $\hat{u}/\hat{v} \rightarrow 0$ (bottom) and $\hat{u}/\hat{v} \rightarrow \infty$ (top), respectively.

Provided the phase difference between the two waves is $\frac{1}{2}\pi$, this means $\delta_\phi - \delta_u = \frac{1}{2}\pi$, one can find a special solution to the linearised equations given by

$$\hat{u} = -\frac{2\mu_c}{Ak} \hat{\phi}, \quad \rho = \frac{k^2(\mu_c(\lambda + 2\mu) - A^2)}{\mu_c \omega^2}, \quad \varrho_{\text{rot}} = \frac{\gamma k^2 + 4A}{\omega^2}. \quad (5-12)$$

This is an interesting result as solutions of this type imply conditions that have to be satisfied regarding the parameters of the theory. There does not exist a nontrivial solution when $\mu_c = 0$; in this case one finds $u = v = \phi = 0$. This is consistent with theoretical considerations since the choice $\mu_c = 0$ is not admitted in the linearised context.

5.3. Other possible applications. Our intrinsic two-dimensional model might be particularly suited to describe materials like graphene and carbon nanotubes. These materials have unusual properties which make them valuable for applications in nanotechnology. The mathematical description of electrons propagating in graphene, for example, requires the use of the two-dimensional massless Dirac equation. The microstructure of Cosserat elasticity lends itself naturally to consider applications in this area, and some research along those lines is ongoing. In [Caillerie et al. 2006] a homogenization was applied to model a graphene sheet, while applications of Cosserat elasticity were considered in [De Cicco and Ieşan 2013] and also [Yang et al. 2016]. Elastic properties of graphene were studied in [Cadelano et al. 2010]. Carbon nanotubes, on the other hand, were studied in the context of Cosserat elasticity in [Selmi et al. 2014]. It will be interesting to apply our approach to some of these models in the future.

6. Conclusions

The primary motivation of this paper was the formulation of an intrinsic two-dimensional, geometrically nonlinear Cosserat theory of elasticity that could be used to model, amongst other features, chiral lattices. Our construction circumvents the problems one faces when reducing a three-dimensional isotropic and chiral theory to the plane. It is well known that the resulting two-dimensional theory is no longer chiral.

Our model is intrinsically two-dimensional and does not refer to a three-dimensional model for its construction. Chirality is introduced into this model by defining a new rotated deformation gradient F^* , see (3-15), which is constructed from the deformation vector rotated by $\frac{1}{2}\pi$ in the counterclockwise direction. This deformation gradient is then used to define a new elastic energy and also new interaction terms between the deformation gradient F and the new quantity F^* . This approach is different to other approaches as we are directly modeling the planar chiral material.

Due to our intrinsic approach, our model displays a certain flexibility in the sense that it depends on up to 10 different elastic constants and the characteristic length L_c . These are the two-dimensional elastic (Lamé) constants μ, λ , the Cosserat couple modulus μ_c , and the interaction term χ . Moreover, we have the corresponding constants $\mu^*, \lambda^*, \mu_c^*$ and finally the three constants m_1, m_2, m_3 . This allows us to formulate previously studied models using our intrinsic approach. It would also be interesting to apply our approach to other two-dimensional materials like graphene.

Finally, let us draw the attention back to the question of how to obtain a chiral two-dimensional model. We have seen that using a quadratic ansatz in the three-dimensional Cosserat model necessarily cannot give a two-dimensional chiral model, no matter our effort. However, it is not clear whether this problematic issue can be avoided by using some higher order (nonquadratic) model in the first place. If this were possible, the chiral effect would be absent under linearization. Therefore, more experimental evidence is needed to decide whether chirality can and should appear already as a discernible effect in an infinitesimal neighborhood of the identity.

Acknowledgement

Bahamonde is supported by the Comisión Nacional de Investigación Científica y Tecnológica (Becas Chile Grant No. 72150066).

Appendix A: Chirality and the matrix curl

Let us define the new deformation vector $\varphi^\#$ by

$$\varphi^\#(x, y, z) := \varphi(-x, -y, -z). \quad (\text{A-1})$$

This means we evaluate the function φ at the inverted coordinate $(-x, -y, -z)$. However, we will work in the original Cartesian coordinate system and will not make the coordinate transformation of the previous appendix. Then, one verifies that

$$F^\# = \nabla \varphi^\# = -\nabla \varphi(-x, -y, -z) = -F(-x, -y, -z), \quad (\text{A-2})$$

because of the chain rule. Under this ‘‘inversion’’ the deformation gradient picks up a sign, making it noninvariant. On the other hand, $F^T F$ is invariant.

Next, let us define the new orthogonal matrix $R^\#$ which we define by

$$R^\# := -R(-x, -y, -z), \quad (\text{A-3})$$

where an additional minus sign was included in the definition. Then one immediately finds $(R^\#)^T = -R(-x, -y, -z)^T = -(R^T)(-x, -y, -z)$ and

$$\text{Curl } R^\# = \begin{pmatrix} \partial_y R^\#_{xz} - \partial_z R^\#_{xy} & \partial_z R^\#_{xx} - \partial_x R^\#_{xz} & \partial_x R^\#_{xy} - \partial_y R^\#_{xx} \\ \partial_y R^\#_{yz} - \partial_z R^\#_{yy} & \partial_z R^\#_{yx} - \partial_x R^\#_{yz} & \partial_x R^\#_{yy} - \partial_y R^\#_{yx} \\ \partial_y R^\#_{zz} - \partial_z R^\#_{zy} & \partial_z R^\#_{zx} - \partial_x R^\#_{zz} & \partial_x R^\#_{zy} - \partial_y R^\#_{zx} \end{pmatrix}. \quad (\text{A-4})$$

Each single derivative will yield a minus sign by virtue of the chain rule. For instance,

$$\partial_y R^\# := -\partial_y R(-x, -y, -z) = \partial_{-y} R(-x, -y, -z) = (\partial_y R)(-x, -y, -z). \quad (\text{A-5})$$

Hence, applying this through all terms in the matrix curl of $R^\#$, one arrives at

$$\text{Curl } R^\# = (\text{Curl } R)(-x, -y, -z). \quad (\text{A-6})$$

Finally, one can study the curvature measure $(R^\#)^T \text{Curl } R^\#$ which satisfies

$$(R^\#)^T \text{Curl } R^\# = -(R^T)(-x, -y, -z)(\text{Curl } R)(-x, -y, -z) = -(R^T \text{Curl } R)(-x, -y, -z). \quad (\text{A-7})$$

This result shows the desired chiral properties. Consequently, we showed that the term $\langle F^T F, R^T \text{Curl } R \rangle$ is chiral.

Appendix B: Variations and equations of motion

Each of the four parts of our energy functional (3-11) and (3-18) are considered separately. The various matrix derivatives that occur in this calculation are computed using standard formulae, all of which can be found nicely presented in [Petersen and Pedersen 2012].

B.1. Elastic energy V_{elastic} . We can rewrite the elastic energy functional as

$$\begin{aligned} V_{\text{elastic}} &= \mu \|\text{sym } \bar{R}^T F - \mathbb{1}\|^2 + \frac{1}{2} \lambda (\text{tr}(\text{sym}(\bar{R}^T F) - \mathbb{1}))^2 \\ &= 2\mu - 2\mu \text{tr}(F \bar{R}^T) + \frac{1}{2} \mu (\text{tr}(\bar{R}^T F \bar{R}^T F) + \text{tr}(F F^T)) \\ &\quad + 2\lambda - 2\lambda \text{tr}(\bar{R}^T F) + \frac{1}{2} \lambda (\text{tr}(\bar{R}^T F))^2. \end{aligned} \quad (\text{B-1})$$

Now we can compute the variations of this energy functional:

$$\begin{aligned} \delta V_{\text{elastic}}(F, \bar{R}) &= \frac{1}{2} \mu \left(\frac{d}{d\bar{R}} [\text{tr}(\bar{R}^T F \bar{R}^T F)] : \delta \bar{R} + \frac{d}{dF} \left[\text{tr}(\bar{R}^T F \bar{R}^T F) + \frac{d}{dF} (\text{tr}(F F^T)) \right] : \delta F \right) \\ &\quad - 2(\mu + \lambda) \left(\frac{d}{d\bar{R}} (\text{tr}(\bar{R}^T F)) : \delta \bar{R} + \frac{d}{dF} (\text{tr}(\bar{R}^T F)) : \delta F \right) \\ &\quad + \frac{1}{2} \lambda \left(\frac{d}{d\bar{R}} [\text{tr}(\bar{R}^T F)]^2 : \delta \bar{R} + \frac{d}{dF} [\text{tr}(\bar{R}^T F)]^2 : \delta F \right). \end{aligned} \quad (\text{B-2})$$

Now, computing the various matrix derivatives yields

$$\begin{aligned} \delta V_{\text{elastic}}(F, \bar{R}) &= \langle \mu (\bar{R} F^T \bar{R} + F) - 2(\mu + \lambda) \bar{R} + \lambda \text{tr}(\bar{R}^T F) \bar{R}, \delta F \rangle \\ &\quad + \langle \mu F \bar{R}^T F - 2(\mu + \lambda) F + \lambda \text{tr}(\bar{R}^T F) F, \delta \bar{R} \rangle. \end{aligned} \quad (\text{B-3})$$

If we want to study the dynamical problem, we will need to subtract the kinetic energy term

$$V_{\text{elastic,kinetic}} = \frac{1}{2}\rho\|\dot{\phi}\|^2. \quad (\text{B-4})$$

Here ρ is the density. If we vary this term we will obtain $\delta V_{\text{elastic,kinetic}} = -\rho\ddot{\phi}\delta\phi$, where we neglected a boundary term when integrating by parts once. Next, using that $\nabla\phi = \mathbb{1} + \nabla u$ implies $\delta\phi = \delta u$. Hence, the elastic kinetic term can finally be written as

$$\delta V_{\text{elastic,kinetic}} = -\rho\ddot{u}\delta u. \quad (\text{B-5})$$

B.2. Curvature energy $V_{\text{curvature}}$. The curvature energy functional depends only on the rotation angle ϑ so that

$$V_{\text{curvature}}(\vartheta) = \mu L_c^2 \|\text{grad } \vartheta\|^2. \quad (\text{B-6})$$

Variations with respect to $\delta\vartheta$ are well known (we are dealing with a standard vector), and one finds

$$\delta V_{\text{curvature}} = -2\mu L_c^2 \text{div}(\text{grad } \vartheta)\delta\vartheta = -2\mu L_c^2 \Delta\vartheta\delta\vartheta, \quad (\text{B-7})$$

where, as before, we have neglected a boundary term. Recall that $\text{div grad } \vartheta$ is the scalar Laplacian $\Delta\vartheta$. If we want to study the dynamical problem, we will need to subtract the kinetic energy term

$$V_{\text{curvature,kinetic}} = \rho_{\text{rot}}\|\dot{\vartheta}\|^2. \quad (\text{B-8})$$

Variations with respect to $\delta\vartheta$ lead to

$$\delta V_{\text{curvature,kinetic}} = -2\rho_{\text{rot}}\ddot{\vartheta}\delta\vartheta, \quad (\text{B-9})$$

up to a boundary term.

B.3. Interaction energy $V_{\text{interaction}}$. The interaction term is

$$V_{\text{interaction}}(F, \bar{R}) = \mu L_c \chi \|\bar{R}^T \text{Curl } \bar{R}\| \text{tr}(\bar{R}^T F) = \mu L_c \chi \|\text{grad } \vartheta\| \text{tr}(\bar{R}^T F). \quad (\text{B-10})$$

Computing the variations with respect to \bar{R} and F yields

$$\begin{aligned} \delta V_{\text{interaction}}(F, \vartheta) &= \mu L_c \chi \text{tr}(\bar{R}^T F) \frac{\text{grad } \vartheta}{\|\text{grad } \vartheta\|} \delta(\text{grad } \vartheta) \\ &\quad + \mu L_c \chi \|\text{grad } \vartheta\| \left(\frac{d}{dF} [\text{tr}(\bar{R}^T F)] : \delta F + \frac{d}{d\bar{R}} [\text{tr}(\bar{R}^T F)] : \delta \bar{R} \right) \\ &= -\mu L_c \chi \frac{\text{grad } \vartheta}{\|\text{grad } \vartheta\|} \text{grad}[\text{tr}(\bar{R}^T F)]\delta\vartheta - \mu L_c \chi \text{tr}(\bar{R}^T F) \text{div} \left[\frac{\text{grad } \vartheta}{\|\text{grad } \vartheta\|} \right] \delta\vartheta \\ &\quad + \mu L_c \chi \langle \|\text{grad } \vartheta\| F, \delta \bar{R} \rangle + \mu L_c \chi \langle \|\text{grad } \vartheta\| \bar{R}, \delta F \rangle, \end{aligned} \quad (\text{B-11})$$

which is probably the most complicated of all terms.

B.4. Cosserat couplings V_{coup} . We have the energy functional of the coupling as follows

$$V_{\text{coupling}}(F, \bar{R}) = \mu_c \|\bar{R}^T \text{polar } F - \mathbb{1}\|^2 = 4\mu_c - 2\mu_c \text{tr}(\bar{R}^T \text{polar } F). \quad (\text{B-12})$$

The variations of $\text{polar } F$ with respect to F are somewhat nonstandard; however, the result is well-known and has been reported for instance in [Chen and Wheeler 1993; Rosati 1999]. In particular, in

two dimensions, the result is straightforward to verify directly. We briefly recall that the polar part of F can be written as polar $F = F(F^T F)^{-1/2}$. Then

$$\delta V_{\text{coupling}}(F, \bar{R}) = -2\mu_c \text{polar } F : \delta \bar{R} - 2\mu_c \left[\frac{d}{dF} (\text{tr}(\bar{R}^T \text{polar } F)) \right] : \delta F. \quad (\text{B-13})$$

Using the chain rule for matrix differentiation we find

$$\begin{aligned} \frac{d}{dF_{ml}} (\text{tr}(\bar{R}^T \text{polar } F)) &= \text{tr} \left[\left(\frac{d}{d \text{polar } F} \text{tr}(\bar{R}^T \text{polar } F) \right)^T \frac{d \text{polar } F}{dF_{ml}} \right] \\ &= \text{tr} \left[\bar{R}^T \frac{d \text{polar } F}{dF_{ml}} \right]. \end{aligned} \quad (\text{B-14})$$

Following [Chen and Wheeler 1993; Rosati 1999] we have

$$\frac{d \text{polar } F}{dF} = \frac{1}{\text{tr}(U)} (\mathbb{I} - \text{polar}(F) \hat{\boxtimes} \text{polar}(F)^T), \quad (\text{B-15})$$

where we followed the notation used in [Rosati 1999]. Recall that U is the positive definite symmetric part of the polar decomposition $F = \text{polar}(F)U$. The symbol $\hat{\boxtimes}$ denotes the operation $(A \hat{\boxtimes} B)_{ijkl} = A_{il}B_{jk}$ for any two matrices A and B . In addition we use the notation $\mathbb{I} = \mathbb{1} \hat{\boxtimes} \mathbb{1}$. Putting this together yields

$$\text{tr} \left[\bar{R}^T \frac{d \text{polar } F}{dF_{ml}} \right] = \frac{1}{\text{tr}(U)} [\bar{R} - R \bar{R}^T R]. \quad (\text{B-16})$$

Finally, we will obtain the variations $\delta V_{\text{coupling}}$, which are given by

$$\delta V_{\text{coupling}}(F, \bar{R}) = -2\mu_c \langle R, \delta \bar{R} \rangle - \frac{2\mu_c}{\text{tr}(U)} \langle \bar{R} - R \bar{R}^T R, \delta F \rangle. \quad (\text{B-17})$$

Now we will focus on the second coupling term (3-10) that can be rewritten as follows

$$V_{\text{coupling}(2)}(F, \bar{R}) = 3\mu_c + \frac{1}{2}\mu_c \text{tr}[F^T F - \bar{R}^T F \bar{R}^T F], \quad (\text{B-18})$$

which yields

$$\delta V_{\text{coupling}(2)}(F, \bar{R}) = \mu_c \langle F - \bar{R} F^T \bar{R}, \delta F \rangle - \mu_c \langle \bar{R}^T F, \delta \bar{R} \rangle. \quad (\text{B-19})$$

B.5. Chiral terms. Let us begin by computing the term $\delta V_{\text{elastic}}^*$. A direct calculation yields

$$\begin{aligned} \delta V_{\text{elastic}}^* &= -\text{Div} \left[\mu^* (\bar{R} (F^*)^T \bar{R} + F^*) - 2(\mu^* + \lambda^*) \bar{R} + \lambda^* \text{tr}(\bar{R}^T F^*) \bar{R} + \mu_c^* (\bar{R} (F^*)^T \bar{R} - F^*) \right] : \epsilon \delta u \\ &+ \left[\mu^* F^* \bar{R}^T F^* - 2(\mu^* + \lambda^*) F^* + \lambda^* \text{tr}(\bar{R}^T F^*) F^* + \mu_c^* F^* \bar{R}^T F^* \right] : (-\epsilon \bar{R}) \delta \vartheta. \end{aligned} \quad (\text{B-20})$$

Next, we consider the mixing terms

$$\begin{aligned} \delta V_{\text{mixing}} &= \frac{1}{2} m_1 (\delta [\text{tr}(\bar{R}^T F^* \bar{R}^T F)] + \delta [\text{tr}(F (F^*)^T)] - 2\delta [\text{tr}(\bar{R}^T F^*) + \text{tr}(\bar{R}^T F)]) \\ &+ m_2 (\delta [\text{tr}(\bar{R}^T F^*) \text{tr}(\bar{R}^T F)] - \delta [\text{tr}(\bar{R}^T F^*) + \text{tr}(\bar{R}^T F)]) \\ &+ \frac{1}{2} m_3 (\delta [\text{tr}(F (F^*)^T)] - \delta [\text{tr}(\bar{R}^T F^* \bar{R}^T F)]). \end{aligned} \quad (\text{B-21})$$

These variations are slightly more involved than the previous ones, so some additional details are given in the following. The first three respective terms are given by

$$\delta[\text{tr}(\bar{R}^T F^* \bar{R}^T F)] = (F \bar{R}^T \epsilon^T F + \epsilon^T F \bar{R} F) : \delta \bar{R} + (\epsilon^T \bar{R} F^T \bar{R} + \bar{R} F^T \epsilon^T \bar{R}) : \delta F, \quad (\text{B-22})$$

$$\delta[\text{tr}(F(F^*)^T)] = F : \delta F^* + F^* : \delta F = [(F : \epsilon) + F^*] : \delta F, \quad (\text{B-23})$$

$$\delta[\text{tr}(\bar{R}^T F^*) + \text{tr}(\bar{R}^T F)] = (\bar{R} : \epsilon + \bar{R}) : \delta F + (F + F^*) : \delta \bar{R}. \quad (\text{B-24})$$

The fourth and final term is given by

$$\delta[\text{tr}(\bar{R}^T F^*) \text{tr}(\bar{R}^T F)] = (\text{tr}(\bar{R}^T F^*) F + \text{tr}(\bar{R}^T F) F^*) : \delta R + (\text{tr}(\bar{R}^T F^*) R + \text{tr}(\bar{R}^T F) (R : \epsilon)) : \delta F. \quad (\text{B-25})$$

Therefore, the complete variations are given by

$$\begin{aligned} \delta V_{\text{mixing}} = & \left[\frac{1}{2} m_1 (F \bar{R}^T \epsilon^T F + \epsilon^T F \bar{R} F - 2(F + F^*)) \right. \\ & + m_2 (\text{tr}(\bar{R}^T F^*) F + \text{tr}(\bar{R}^T F) F^* - (F + F^*)) - \frac{1}{2} m_3 (F \bar{R}^T \epsilon^T F + \epsilon^T F \bar{R} F) \left. \right] : \delta \bar{R} \\ & + \left[\frac{1}{2} m_1 (\epsilon^T \bar{R} F^T \bar{R} + \bar{R} (F^*)^T \bar{R} + F : \epsilon + F^* - 2(\bar{R} : \epsilon + \bar{R})) \right. \\ & + m_2 (\text{tr}(\bar{R}^T F^*) R + \text{tr}(\bar{R}^T F) (R : \epsilon) - (\bar{R} : \epsilon + \bar{R})) \\ & \left. + \frac{1}{2} m_3 (F : \epsilon + F^* - (F \bar{R}^T \epsilon^T F + \epsilon^T F \bar{R} F)) \right] : \delta F. \quad (\text{B-26}) \end{aligned}$$

List of Symbols

$\mathbb{1}$	identity matrix
φ	deformation vector in 3D and 2D
ϕ	rotation angle in 3D
\mathbf{u}	displacement vector
\mathbf{a}	rotation vector
$F = \nabla \varphi = I + \nabla \mathbf{u}$	deformation gradient
$F_{ij} = \delta_{ij} + \mathbf{u}_{i,j} = \delta_{ij} + \partial_j \mathbf{u}_i$	deformation gradient in index notation
$\bar{R} = \exp(\bar{A})$	rotation matrix
\bar{A}	skew-symmetric matrix generating \bar{R}
ϵ	2D Levi-Civita symbol, $\epsilon_{12} = 1 = -\epsilon_{21}$, $\epsilon_{11} = \epsilon_{22} = 0$
$\bar{U} = \bar{R}^T F$	nonsymmetric stretch tensor, first Cosserat deformation tensor
$F = RU = \text{polar}(F)U$	classical polar decomposition
$(\text{Curl } M)_i = \epsilon_{rs} \partial_r M_{is}$	matrix curl in 2D
$(\text{Div } M)_i = \partial_s M_{is}$	matrix divergence in 2D
$\text{sym } M = \frac{1}{2}(M + M^T)$	symmetric part of matrix M
$\text{skew } M = \frac{1}{2}(M - M^T)$	skew-symmetric part of M
$\text{dev } M = M - \frac{1}{3} \text{tr}(M) \mathbb{1}$	deviatoric or trace-free part of M
ϑ	rotation angle in 2D
$\bar{R} = (\cos \vartheta) \mathbb{1} - (\sin \vartheta) \epsilon$	rotation in 2D

Remark. We write the above tensors \bar{R} and \bar{U} with superposed bars in order to distinguish them from the factors R and U of the classical polar decomposition $F = RU$, in which $R = \text{polar } F$ is orthogonal and U is positive definite, symmetric, and is a standard notation in elasticity. We also note the standard relation $F^T F = (RU)^T (RU) = U^T R^T T U = U^T U = U^2$ so that $U = \sqrt{F^T F}$.

We will use the Frobenius scalar product defined as

$$\langle A, B \rangle = A : B = A_{ij} B_{ij} = \text{tr}(AB^T). \quad (\text{B-27})$$

References

- [Birsan and Neff 2013] M. Birsan and P. Neff, “Existence theorems in the geometrically non-linear 6-parameter theory of elastic plates”, *J. Elasticity* **112**:2 (2013), 185–198.
- [Birsan and Neff 2014] M. Birsan and P. Neff, “Existence of minimizers in the geometrically non-linear 6-parameter resultant shell theory with drilling rotations”, *Math. Mech. Solids* **19**:4 (2014), 376–397.
- [Böhmer and Obukhov 2012] C. G. Böhmer and Y. N. Obukhov, “A gauge-theoretical approach to elasticity with microrotations”, *Proc. R. Soc. Lond. A* **468**:2141 (2012), 1391–1407.
- [Böhmer and Tamanini 2015] C. G. Böhmer and N. Tamanini, “Rotational elasticity and couplings to linear elasticity”, *Math. Mech. Solids* **20**:8 (2015), 959–974.
- [Böhmer et al. 2011] C. G. Böhmer, R. J. Downes, and D. Vassiliev, “Rotational elasticity”, *Quart. J. Mech. Appl. Math.* **64**:4 (2011), 415–439.
- [Böhmer et al. 2016] C. G. Böhmer, P. Neff, and B. Seymenoğlu, “Soliton-like solutions based on geometrically nonlinear Cosserat micropolar elasticity”, *Wave Motion* **60** (2016), 158–165.
- [Borisov et al. 2016] L. Borisov, A. Fischle, and P. Neff, “Optimality of the relaxed polar factors by a characterization of the set of real square roots of real symmetric matrices”, preprint, 2016.
- [Cadelano et al. 2010] E. Cadelano, P. L. Palla, S. Giordano, and L. Colombo, “Elastic properties of hydrogenated graphene”, *Phys. Rev. B* **82** (2010), art. id. 235414.
- [Caillerie et al. 2006] D. Caillerie, A. Mourad, and A. Raoult, “Discrete homogenization in graphene sheet modeling”, *J. Elasticity* **84**:1 (2006), 33–68.
- [Chen and Wheeler 1993] Y.-C. Chen and L. Wheeler, “Derivatives of the stretch and rotation tensors”, *J. Elasticity* **32**:3 (1993), 175–182.
- [Chen et al. 2014] Y. Chen, X. N. Liu, G. K. Hu, Q. P. Sun, and Q. S. Zheng, “Micropolar continuum modeling of bi-dimensional tetrachiral lattices”, *Proc. R. Soc. Lond. A* **470**:2165 (2014), art. id. 20130734.
- [Cheverton and Beatty 1981] K. J. Cheverton and M. F. Beatty, “Extension, torsion and expansion of an incompressible, hemitropic Cosserat circular cylinder”, *J. Elasticity* **11**:2 (1981), 207–227.
- [Cosserat and Cosserat 1909] E. Cosserat and F. Cosserat, *Théorie des corps déformables*, Hermann, Paris, 1909.
- [De Cicco and Ieşan 2013] S. De Cicco and D. Ieşan, “A theory of chiral Cosserat elastic plates”, *J. Elasticity* **111**:2 (2013), 245–263.
- [Ericksen 1962a] J. L. Ericksen, “Hydrostatic theory of liquid crystals”, *Arch. Ration. Mech. Anal.* **9** (1962), 371–378.
- [Ericksen 1962b] J. L. Ericksen, “Kinematics of macromolecules”, *Arch. Ration. Mech. Anal.* **9** (1962), 1–8.
- [Ericksen 1967] J. L. Ericksen, “Twisting of liquid crystals”, *J. Fluid Mech.* **27**:1 (1967), 59–64.
- [Ericksen and Truesdell 1957] J. L. Ericksen and C. Truesdell, “Exact theory of stress and strain in rods and shells”, *Arch. Ration. Mech. Anal.* **1** (1957), 295–323.
- [Eringen 1999] A. C. Eringen, *Microcontinuum field theories, I: Foundations and solids*, Springer, 1999.
- [Eringen and Suhubi 1964] A. C. Eringen and E. S. Suhubi, “Nonlinear theory of simple micro-elastic solids, I”, *Int. J. Eng. Sci.* **2** (1964), 189–203.

- [Fischle and Neff 2017a] A. Fischle and P. Neff, “The geometrically nonlinear Cosserat micropolar shear-stretch energy, I: A general parameter reduction formula and energy-minimizing microrotations in 2D”, *Z. Angew. Math. Mech.* **97**:7 (2017), 828–842.
- [Fischle and Neff 2017b] A. Fischle and P. Neff, “The geometrically nonlinear Cosserat micropolar shear-stretch energy, II: Non-classical energy-minimizing microrotations in 3D and their computational validation”, *Z. Angew. Math. Mech.* **97**:7 (2017), 843–871.
- [Fischle and Neff 2017c] A. Fischle and P. Neff, “Grioli’s theorem with weights and the relaxed-polar mechanism of optimal Cosserat rotations”, *Rend. Accad. Naz. Lincei* **28**:3 (2017), 573–600.
- [Fischle et al. 2017] A. Fischle, P. Neff, and D. Raabe, “The relaxed-polar mechanism of locally optimal Cosserat rotations for an idealized nanoindentation and comparison with 3D-EBSD experiments”, *Z. Angew. Math. Phys.* **68**:4 (2017), art. id. 90.
- [Green and Rivlin 1964] A. E. Green and R. S. Rivlin, “Multipolar continuum mechanics”, *Arch. Ration. Mech. Anal.* **17** (1964), 113–147.
- [Joumaa and Ostoja-Starzewski 2011] H. Joumaa and M. Ostoja-Starzewski, “Stress and couple-stress invariance in non-centrosymmetric micropolar planar elasticity”, *Proc. R. Soc. Lond. A* **467**:2134 (2011), 2896–2911.
- [Lakes 2001] R. S. Lakes, “Elastic and viscoelastic behavior of chiral materials”, *Int. J. Mech. Sci.* **43**:7 (2001), 1579–1589.
- [Lakes and Benedict 1982] R. S. Lakes and R. L. Benedict, “Noncentrosymmetry in micropolar elasticity”, *Int. J. Eng. Sci.* **20**:10 (1982), 1161–1167.
- [Lankeit et al. 2017] J. Lankeit, P. Neff, and F. Osterbrink, “Integrability conditions between the first and second Cosserat deformation tensor in geometrically nonlinear micropolar models and existence of minimizers”, *Z. Angew. Math. Phys.* **68**:1 (2017), art. id. 11.
- [Liu and Hu 2016] X. N. Liu and G. K. Hu, “Elastic metamaterials making use of chirality: a review”, *J. Mech. Eng.* **62**:7-8 (2016), 403–418.
- [Liu et al. 2012a] X. N. Liu, G. L. Huang, and G. K. Hu, “Analytical formation of a discrete chiral elastic metamaterial model”, art. id. 834823 in *Health monitoring of surgical and biological systems* (San Diego, 2012), edited by T. Kundu, SPIE Proceedings **8348**, SPIE, Bellingham, WA, 2012.
- [Liu et al. 2012b] X. N. Liu, G. L. Huang, and G. K. Hu, “Chiral effect in plane isotropic micropolar elasticity and its application to chiral lattices”, *J. Mech. Phys. Solids* **60**:11 (2012), 1907–1921.
- [Mindlin 1964] R. D. Mindlin, “Micro-structure in linear elasticity”, *Arch. Ration. Mech. Anal.* **16**:1 (1964), 51–78.
- [Münch et al. 2011] I. Münch, P. Neff, and W. Wagner, “Transversely isotropic material: nonlinear Cosserat versus classical approach”, *Contin. Mech. Therm.* **23**:1 (2011), 27–34.
- [Neff 2004a] P. Neff, “Existence of minimizers for a geometrically exact Cosserat solid”, *Proc. Appl. Math. Mech.* **4**:1 (2004), 548–549.
- [Neff 2004b] P. Neff, “A geometrically exact Cosserat shell-model including size effects, avoiding degeneracy in the thin shell limit, I: Formal dimensional reduction for elastic plates and existence of minimizers for positive Cosserat couple modulus”, *Contin. Mech. Therm.* **16**:6 (2004), 577–628.
- [Neff 2006a] P. Neff, “Existence of minimizers for a finite-strain micromorphic elastic solid”, *Proc. Roy. Soc. Edinburgh A* **136**:5 (2006), 997–1012.
- [Neff 2006b] P. Neff, “A finite-strain elastic-plastic Cosserat theory for polycrystals with grain rotations”, *Int. J. Eng. Sci.* **44**:8-9 (2006), 574–594.
- [Neff 2007] P. Neff, “A geometrically exact planar Cosserat shell-model with microstructure: existence of minimizers for zero Cosserat couple modulus”, *Math. Models Methods Appl. Sci.* **17**:3 (2007), 363–392.
- [Neff and Münch 2008] P. Neff and I. Münch, “Curl bounds grad on $SO(3)$ ”, *ESAIM Control Optim. Calc. Var.* **14**:1 (2008), 148–159.
- [Neff and Münch 2009] P. Neff and I. Münch, “Simple shear in nonlinear Cosserat elasticity: bifurcation and induced microstructure”, *Contin. Mech. Therm.* **21**:3 (2009), 195–221.
- [Neff et al. 2008] P. Neff, A. Fischle, and I. Münch, “Symmetric Cauchy stresses do not imply symmetric Biot strains in weak formations of isotropic hyperelasticity with rotational degrees of freedom”, *Acta Mech.* **197**:1-2 (2008), 19–30.

- [Neff et al. 2010] P. Neff, K.-I. Hong, and J. Jeong, “The Reissner–Mindlin plate is the Γ -limit of Cosserat elasticity”, *Math. Models Methods Appl. Sci.* **20**:9 (2010), 1553–1590.
- [Neff et al. 2015] P. Neff, M. Bîrsan, and F. Osterbrink, “Existence theorem for geometrically nonlinear Cosserat micropolar model under uniform convexity requirements”, *J. Elasticity* **121**:1 (2015), 119–141.
- [Ostoja-Starzewski and Jasiuk 1995] M. Ostoja-Starzewski and I. Jasiuk, “Stress invariance in planar Cosserat elasticity”, *Proc. R. Soc. Lond. A* **451**:1942 (1995), 453–470.
- [Petersen and Pedersen 2012] K. B. Petersen and M. S. Pedersen, “The matrix cookbook”, preprint, Technical Univ. Denmark, 2012, available at www2.imm.dtu.dk/pubdb/p.php?3274.
- [Rosati 1999] L. Rosati, “Derivatives and rates of the stretch and rotation tensors”, *J. Elasticity* **56**:3 (1999), 213–230.
- [Rosi and Auffray 2016] G. Rosi and N. Auffray, “Anisotropic and dispersive wave propagation within strain-gradient framework”, *Wave Motion* **63** (2016), 120–134.
- [Sander et al. 2016] O. Sander, P. Neff, and M. Bîrsan, “Numerical treatment of a geometrically nonlinear planar Cosserat shell model”, *Comput. Mech.* **57**:5 (2016), 817–841.
- [Schaefer 1967] H. Schaefer, “Das Cosserat Kontinuum”, *Z. Angew. Math. Mech.* **47**:8 (1967), 485–498.
- [Selmi et al. 2014] A. Selmi, H. Hassis, I. Doghri, and H. Zenzri, “A Cosserat-type plate theory and its application to carbon nanotube microstructure”, *Amer. J. Appl. Sci.* **11**:8 (2014), 1255–1273.
- [Suhubi and Eringen 1964] E. S. Suhubi and A. C. Eringen, “Nonlinear theory of micro-elastic solids, II”, *Int. J. Eng. Sci.* **2** (1964), 389–404.
- [Toupin 1962] R. A. Toupin, “Elastic materials with couple-stresses”, *Arch. Ration. Mech. Anal.* **11** (1962), 385–414.
- [Toupin 1964] R. A. Toupin, “Theories of elasticity with couple-stress”, *Arch. Ration. Mech. Anal.* **17** (1964), 85–112.
- [Yang et al. 2016] G. Yang, Z. Huang, C.-F. Gao, and B. Zhang, “Theoretical consideration of a microcontinuum model of graphene”, *AIP Adv.* **6**:5 (2016), art. id. 055115.

Received 13 May 2017. Revised 9 Aug 2017. Accepted 14 Aug 2017.

SEBASTIAN BAHAMONDE: sebastian.beltran.14@ucl.ac.uk
 Department of Mathematics, University College London, London, United Kingdom

CHRISTIAN G. BÖHMER: c.boehmer@ucl.ac.uk
 Department of Mathematics, University College London, London, United Kingdom

PATRIZIO NEFF: patrizio.neff@uni-due.de
 Lehrstuhl für Nichtlineare Analysis und Modellierung, Fakultät für Mathematik, Universität Duisburg-Essen, Essen, Germany

JOURNAL OF MECHANICS OF MATERIALS AND STRUCTURES

msp.org/jomms

Founded by Charles R. Steele and Marie-Louise Steele

EDITORIAL BOARD

ADAIR R. AGUIAR	University of São Paulo at São Carlos, Brazil
KATIA BERTOLDI	Harvard University, USA
DAVIDE BIGONI	University of Trento, Italy
YIBIN FU	Keele University, UK
IWONA JASIUK	University of Illinois at Urbana-Champaign, USA
MITSUTOSHI KURODA	Yamagata University, Japan
C. W. LIM	City University of Hong Kong
THOMAS J. PENCE	Michigan State University, USA
GIANNI ROYER-CARFAGNI	Università degli studi di Parma, Italy
DAVID STEIGMANN	University of California at Berkeley, USA
PAUL STEINMANN	Friedrich-Alexander-Universität Erlangen-Nürnberg, Germany

ADVISORY BOARD

J. P. CARTER	University of Sydney, Australia
D. H. HODGES	Georgia Institute of Technology, USA
J. HUTCHINSON	Harvard University, USA
D. PAMPLONA	Universidade Católica do Rio de Janeiro, Brazil
M. B. RUBIN	Technion, Haifa, Israel

PRODUCTION production@msp.org

SILVIO LEVY Scientific Editor

Cover photo: Wikimedia Commons

See msp.org/jomms for submission guidelines.

JoMMS (ISSN 1559-3959) at Mathematical Sciences Publishers, 798 Evans Hall #6840, c/o University of California, Berkeley, CA 94720-3840, is published in 10 issues a year. The subscription price for 2017 is US \$615/year for the electronic version, and \$775/year (+\$60, if shipping outside the US) for print and electronic. Subscriptions, requests for back issues, and changes of address should be sent to MSP.

JoMMS peer-review and production is managed by EditFLOW® from Mathematical Sciences Publishers.

PUBLISHED BY

 **mathematical sciences publishers**
nonprofit scientific publishing

<http://msp.org/>

© 2017 Mathematical Sciences Publishers

Journal of Mechanics of Materials and Structures

Volume 12, No. 5

December 2017

- Nonlinear impacting oscillations of pipe conveying pulsating fluid subjected to distributed motion constraints**
WANG YIKUN, NI QIAO, WANG LIN, LUO YANGYANG and YAN HAO 563
- Micro and macro crack sensing in TRC beam under cyclic loading** YISKA
GOLDFELD, TILL QUADFLIEG, STAV BEN-AAROSH and THOMAS GRIES 579
- Static analysis of nanobeams using Rayleigh–Ritz method**
LAXMI BEHERA and S. CHAKRAVERTY 603
- Analysis of pedestrian-induced lateral vibration of a footbridge that considers feedback adjustment and time delay**
JIA BUYU, CHEN ZHOU, YU XIAOLIN and YAN QUANSHENG 617
- Nearly exact and highly efficient elastic-plastic homogenization and/or direct numerical simulation of low-mass metallic systems with architected cellular microstructures** MARYAM TABATABAEI, DY LE and SATYA N. ATLURI 633
- Transient analysis of fracture initiation in a coupled thermoelastic solid**
LOUIS M. BROCK 667
- Geometrically nonlinear Cosserat elasticity in the plane: applications to chirality**
SEBASTIAN BAHAMONDE, CHRISTIAN G. BÖHMER and PATRIZIO NEFF 689
- Transient response of multilayered orthotropic strips with interfacial diffusion and sliding**
XU WANG and PETER SCHIAVONE 711



1559-3959(2017)12:5;1-0